

**PROPRIETES**

Laque brillante pour travaux d'intérieur ou d'extérieur  
Pigmentation stable à la lumière  
Système d'application aisé, facile à travailler, à séchage rapide  
S'applique en plusieurs couches de faibles épaisseurs

**UTILISATION**

Finition automobile et industrielle  
Laquage des meubles et des boiseries

**CARACTERISTIQUES**

Présentation	:	Mono-composant
Liant	:	Nitro synthétique
Pigmentation	:	Pigment résistant à la lumière
Aspect	:	Brillant
Couleur	:	Teintes nuancier métallisé
Densité	:	1,15 Kg / L ± 0,15
Viscosité à 25°C	:	105 Ku ± 5
Extrait sec en poids	:	52 % ± 5
Rendement théorique	:	7 m <sup>2</sup> / Kg
Epaisseur du film recommandée	:	30 microns
Séchage à 20°C	:	30 min
60° hygro	:	1 h
Relative	:	2 h
Conditionnement	:	1 Kg
Stockage	:	1 an en emballage d'origine

**PREPARATION**

Le support doit être sain, propre et dégraissé.  
Dans le cas contraire, on utilisera une solution dégraissante  
Appliquer le produit sur :

- Appret Filler 199Z+
- Appret 132N
- Mono Filler 3o1

**APPLICATION**

Matériel : Pistolet pneumatique ou HVLP  
Diluant : V18  
Dilution en poids : 40 - 60 %  
Dilution en volume : 45 - 65 %  
Pour donner de profondeur et du brillant,  
une couche de VERNIS 20Z2 est recommandée



**PROPERTIES**

Bright finishing for interior and exterior work  
UV resistance pigmentation  
Easy and fast drying application system  
It is applied in multi-layered thin coat

**UTILIZATION**

Automotive & industrial refinish  
Finish products for furniture & woodwork

**CHARACTERISTICS**

Presentation	: 1K
Binder	: Nitro synthetic
Pigmentation	: UV Resistant pigment
Aspect of dry film	: bright
Colors	: Metal color chart
Density	: 1,15 Kg/L +/- 0,15
(depends by the Color)	
Viscosity at 20 °C	: 105 sec KU +/- 5
Dry extract in weight	: 52% +/- 5
Theoretical Yield	: 7 M2/L
Recommended film thickness	: 30 microns
Drying at 20°C	
	• <b>Dust Free</b> : 30 Min
	• <b>Handleable</b> : 1 H
	• <b>Hard Dry</b> : 2 H
Packaging	: 1 Kg
Shelf Life	: 1 year in original packaging

**PREPARATION**

The support have to be sand, clean and degreased  
Otherwise use a solvent degreaser  
Apply on :

- Appret Filler 199Z+
- Appret 132N
- Mono Filler 3o1

**APPLICATION**

Equipment	: Gravity spray gun or HVLP
Thinner	: V18
Thinning in weight	: 40 - 60 %
Thinning in volume	: 45 - 65 %

In order to have higher gloss is suggested a coat  
of VERNIS 20Z2

