

VERNIS 2022 + DURCISSEUR 2022

VERNIS ACRYLIQUE 2K MS

PROPRIETES

Vernis Medium solid à brillance élevée, d'excellente tenue aux ultra-violets et aux intempéries
Très bonne tenue aux agents chimiques et aux hydrocarbures

UTILISATION

Vernis top coat pour système bi-couche
Finition industrielle, satisfait particulièrement aux exigences les plus élevées et toute le boiserie intérieures et extérieures.

CARACTERISTIQUES

Présentation	: Bi-composant
Liant	: Acrylique hydroxylé
Aspect	: Brillance élevée
Couleur	: Incolore
Densité	: 1 Kg / L ± 0,020
Extrait sec en poids	: 50% ± 3
Viscosité	: 50 sec ± 5 ISO6
Rendement théorique	: 7 à 8 m ² / L
Epaisseur sec recommandée	: 40 microns
Séchage à 20°C	
	• <i>hors poussière</i> : 30 min
	• <i>sec manipulable</i> : 5 h
	• <i>sec recouvrable</i> : 12 h
Séchage à 60°C	: 30 min
Durée de vie du mélange	: 10 h à 20°C
Conditionnement	: Base 1 L et Durcisseur 0,5 L Base 0,5 L et Durcisseur 0,250 L
Stockage	: 1 an en emballage d'origine.

PREPARATION

Mélanger intimement la base et le catalyseur et laisser mûrir
10 minutes avant l'application et dilution
Ne vernir que sur des fonds propres et secs
Produit sensible à l'humidité

APPLICATION

Matériel	: Pistolet pneumatique ou HVPL
Diluant	: V3
Dilution en volume	: 10 à 20%



VERNIS 2022 + DURCISSEUR 2022

ACRYLIC CLEAR 2K MS

PROPERTIES

Medium solid acrylic clear
High gloss and excellent UV resistance
Good resistance at weathering, chemicals and hydrocarbons

UTILIZATION

Automotive refinish clear for 2 coat system,
Industrial refinish satisfy demanding of vehicles and
Wood Work interior and exterior.

CHARACTERISTICS

Presentation	: Two-pack
Binder	: Acrylic hydroxylated
Aspect of dry film	: high gloss
Colors	: transparent
Density	: 1 Kg/L +/- 0,02
Viscosity at 20 °C	: 50 Sec +/- 5 ISO 6
Dry extract in weight	: 50% +/- 3
Theoretical Yield	: 7-8M2/L
Reccomended thickness	: 40 microns
Drying at 20°C	
	• Dust Free : 30 Min
	• Handleable : 5 H
	• Hard Dry : 12 H
Drying at 60°C	: 30 Min
Pot Life of Mix	: 10 H at 20°C
Packaging	: Clear 1 L - Hardener 0,5 L : Clear 0,5 L - Hardener 0,250 L
Shelf Life	: 1 year in original packaging

PREPARATION

Mix clear and hardener and let stand for 10 Minutes
before thinning and apply.
Apply on surface clean and dry.
The product is sensible at humidity.

APPLICATION

Equipment	: Gravity spray gun or HVPL
Thinner	: V3
Thinning in volume	: 10-20%

